

# A NEW PERSPECTIVE ON THE ROLE OF FIBER PROPERTIES IN COMFORT

Barbara J. Brown, Barry V. Holcombe, A. Mariette Plante, and Anna M. Schneider  
CSIRO Division of Wool Technology - Sydney Laboratory,  
1-11 Anzac Avenue, Ryde, NSW, 2112, Australia.

## INTRODUCTION

Interest in the area of clothing comfort is increasing as its importance to consumers is recognized [1-4]. Studies of clothing comfort based exclusively on the measurement of physiological parameters have been unable to identify any interaction between fiber type and metabolic performance [5,6]. This is mainly because the body sees clothing as a resistance to heat and moisture transfer, and these parameters are determined by fabric construction rather than fiber properties. The use of human sensory perception analysis [7] enables subtle differences between fabric properties to be distinguished. The present paper describes how this technique has been utilised to investigate the role of fiber properties on parameters which contribute to the perception of comfort.

## METHOD

The general details of the procedure have been described in detail elsewhere [7]. Experimental garments were worn by 30 subjects who rated a number of different descriptive terms appropriate to clothing comfort. Grouping of these descriptive terms during analysis provides information about the moisture, surface, and handle/fit characteristics of a fabric. Trials have been conducted to study the influence of fabric surface energy and fiber hygroscopicity on the perception of these descriptors. In both instances, the fabric was lightweight knitwear, made up into a spencer (a skin contact, long sleeved undershirt).

In the first trial, the surface energy of 100% wool fabric was increased by chlorination or decreased by the addition of a hydrophobic fluorocarbon based product. Both treatments modify fiber properties such as surface friction and surface structure as well as surface energy, and this factor must be considered in the interpretation of the experimental data.

The second trial compared a series of blend fabrics whose fiber contents increased in steps of 25% from 100% wool to 100% acrylic. After initial dry cleaning, these fabrics were found to have similar surface energies. A comparison of the subjective evaluations of these fabrics identified differences which could be attributed largely to fabric hygroscopicity.

In both trials, fabrics and garments were very carefully matched in all possible aspects of construction and fit so that the influence of steady-state heat and moisture transport properties could be minimized. Evaluation took place in both sweating and non-sweating conditions for the surface energy experiments, and in sweating conditions only for the hygroscopicity experiments. Surface energy was ranked by means of a modified drop test which measures the length of time for 30µl of a liquid of known surface characteristics to be absorbed into the fabric.

## RESULTS

During conditions of light sweating, subjects perceived descriptors associated with moisture, such as stickiness, dampness, clinginess, clamminess, absorbency and breathability, more intensely as the surface energy of the fabric decreased. As only very small quantities of liquid sweat were present on the skin during the greater part of the trial cycle, these differences cannot be directly attributed to differences in the wicking behaviour of the fabrics. Such differences are believed to be the result of the higher surface energy changing the way moisture is perceived by the skin. There are several mechanisms which could be contributing to this, and work is in progress to clarify this hypothesis. There were no significant differences ( $P > 0.05$ ) perceived in the tactile properties of the fabrics (prickliness, scratchiness) when evaluated under these conditions.

When the same garments were evaluated during non-sweating conditions, only the tactile-related parameters were perceived as differing significantly between garments. The overall mean values for these

descriptors were compared to those obtained **during** light sweating conditions. It was found that **although** light sweating increased tactile-related discomfort, there were no significant differences between garments while moisture-related sensations were present. This indicates that the presence **of** moisture in **d e** clothing microclimate dominates other sensations typically perceived **during** wear.

The second *trial* used conditions of **light** sweating to compare the perception **of** fabrics **of** varying hygroscopicity but constant surface energy. These fabrics were perceived **as** having **similar** moisture-related properties, **but** differed **significantly** in tactile sensations. These differences corresponded to small dimensional changes which occurred **as** a result of laundering between **wearings**, with **d e** looser garments being less scratchy, prickly, etc. The lack of perceived differences in **d e** moisture-related descriptors suggests **that**, during conditions **of** light sweating, **d e** hygroscopicity of **this** fabric construction did not **significantly** influence **d e** perceived moisture sensations.

Hygroscopicity has been shown to have a **significant** influence on **d e** perception of thermal sensations, **coolness** in particular, during non-sweating conditions [8]. These differences were most noticeable when the fabrics were brought into momentary contact with **d e** skin and then removed. This sequence causes **desorption** to occur in the hygroscopic fibers, which is **sufficient** for subjects to rate the hygroscopic fabric **as** cooler than a matched non-hygroscopic fabric. This enhanced coolness was perceived for a range of warm humid **conditions** in the absence **of** thermoregulatory sweating.

## CONCLUSION

The use of human sensory perception techniques **has** shown how fiber properties **can** affect the perception of parameters **that** relate to garment **comfort**. It has been found that when liquid moisture is present in the clothing microclimate, fiber surface energy **has** a significant influence **on** garment **comfort**. During non-sweating conditions, neither fiber surface energy nor hygroscopicity **has** a perceivable effect **on** moisture-related comfort sensations. However, under these conditions, other characteristics of **d e** fabric, such **as** **d e** tactile properties, become more noticeable to **d e** wearer. It **has** been shown that **hygroscopicity** influences the perception of thermal sensations in non-sweating conditions.

## REFERENCES

1. Hatch, K.L., Woo, S.S., Barker, R.L., Radhakrishnaiah, P., Markee, N.L., and Maibach, H.I., In vivo cutaneous and perceived comfort response to fabric, Part I. *Text Res J.*, **60**: 405-412, 1990.
2. Nielsen, R., and Endrusick, T.L., Sensations of temperature and humidity during alternate work/rest and **d e** influence of underwear knit structure. *Ergonomics*, **33**: 221-234, 1990.
3. Sweeney, M.M., and Branson, D.H., Sensorial comfort, Part I, *Text Res J.*, **60**: 371-377, 1990.
4. Umbach, K.-H., Changes in the wear comfort of clothing due to the effects of wear and care. *Melliand Textilberichte* **70**: E206-E209 (English translation of 492-498), 1989.
5. Holmer, I., Heat exchange and dermal insulation compared in woolen and nylon garments during wear trials. *Text Res. J.*, **55**: 511-518, 1985.
6. Rodwell, E.C., Renbourn, E.T., Greenland, J. and Kenchington, K.W.L., An investigation of the physiological value of sorption heat in clothing assemblies. *J. Text. Inst.*, **56**: T624-645, 1965.
7. Hollies, N.R.S., Custer, A.G., Morin, C.J. and Howard, M.E., A human perception analysis approach to clothing comfort, *Text. Res. J.*, **49**: 557-564, 1979.
8. Schneider, A.M. and Holcombe, B.V., Coolness of 'Cool Wool' fabrics. 8th Int. Wool Text. Res. Conf., Christchurch, NZ, 1990.